



BELZONA® 1141 (CONDUCTIVE METAL)

INSTRUCTIONS FOR USE

1. TO ENSURE AN EFFECTIVE MOLECULAR WELD

APPLY ONLY TO CLEAN, FIRM, DRY AND WELL ROUGHENED SURFACES

- Brush away loose contamination and degrease with a rag soaked in **Belzona® 9111** (cleaner/degreaser) or any other effective cleaner which does not leave a residue e.g. methyl ethyl ketone (MEK). Use a flame to sweat out oil from deeply impregnated surfaces.
- Roughen surfaces by blast cleaning, deeply scoring or grinding. This surface preparation should ensure complete removal of all paint and oxide films for electrical contact with substrate.
- Finally degrease again. Use clean rags to avoid spreading contamination.

WHERE BELZONA® 1141 SHOULD NOT ADHERE

Brush on a thin layer of **Belzona® 9411** (Release Agent) and allow to dry for 15-20 minutes before proceeding to step 2.

2. COMBINING THE REACTIVE COMPONENTS

Transfer the entire contents of the Base and Solidifier modules on to the **Belzona® Working Surface**. Mix thoroughly together to achieve a uniform material free of any streakiness.

1. MIXING AT LOW TEMPERATURES

To ease mixing when the material temperature is below 41°F (5°C), warm the Base and Solidifier modules until the contents attain a temperature of 68-77°F (20-25°C).

2. WORKING LIFE

From the commencement of mixing, **Belzona® 1141** must be used within the times shown below.

| Temperature | 41°F (5°C) | 59°F (15°C) | 77°F (25°C) |
|-------------------------|------------|-------------|-------------|
| Use all material within | 60 min. | 40 min. | 25 min. |

3. MIXING SMALL QUANTITIES

For mixing small quantities of **Belzona® 1141** use:
3.0 parts Base to 1 part Solidifier by volume
4.3 parts Base to 1 part Solidifier by weight

4. VOLUME CAPACITY OF MIXED BELZONA® 1141

51 cu.in. (833 cm³) per kg.

3. APPLYING BELZONA® 1141

FOR BEST RESULTS

Do not apply when:

- The temperature is below 41°F (5°C) or the relative humidity is above 90%.
- Rain, snow, fog or mist is present.
- There is moisture on the metal surface or is likely to be deposited by subsequent condensation.
- The working environment is likely to be contaminated by oil/grease from adjacent equipment or smoke from kerosene heaters or tobacco smoking.

FOR REBUILDING

- Apply the **Belzona® 1141** directly on to the prepared surface with the plastic applicator or spatula provided. Press down firmly to fill all cracks, remove entrapped air, and ensure maximum contact with the surface.
- Contour the **Belzona® 1141** to the correct profile with the plastic applicator or alternatively allow to cure and then machine down.

FOR BONDING

- a) Apply a thin smear of **Belzona® 1141** to both bonding surfaces.
- b) Press together to exude excess **Belzona® 1141** and scrape away.

FOR REPAIRING

- a) Spread the **Belzona® 1141** on to the **Belzona® 9341** (Reinforcement Tape).
- b) Apply the bandage to the area to be repaired with the coated side adjacent to the substrate.
- c) Apply a final coat of **Belzona® 1141** on top of the **Belzona® 9341**.

CLEANING

Mixing tools should be cleaned immediately after use with **Belzona® 9111** or any other effective solvent e.g. Methyl ethyl ketone (MEK). Brushes, injection guns, spray equipment and any other application tools should be cleaned using a suitable solvent such as **Belzona® 9121**, MEK, acetone or cellulose thinners.

4. COMPLETION OF THE MOLECULAR REACTION

Allow **Belzona® 1141** to solidify as below subjecting it to the conditions indicated.

| Temperature | Movement or use involving no loading or immersion | Machining and/or light loading | Full electrical, mechanical or thermal loading | Immersion in chemicals |
|-------------|---|--------------------------------|--|------------------------|
| 50°F/10°C | 10 hours | 1 day | 3 days | 12 days |
| 59°F/15°C | 5 hours | 12 hours | 2 days | 7 days |
| 68°F/20°C | 2½ hours | 4 hours | 1 day | 4 days |
| 77°F/25°C | 2 hours | 3 hours | 16 hours | 2½ days |
| 86°F/30°C | 1 hour | 2½ hour | 12 hours | 1½ day |

These times are for a thickness of approximately 0.25 in (6 mm); they will be reduced for thicker sections and extended for thinner sections.

5. APPLICATION OF A FURTHER LAYER OF BELZONA® 1141

When a further layer of **Belzona® 1141** is required, this should be applied as soon as possible after the first layer. Once **Belzona® 1141** has become dimensionally stable then the surface must be roughened otherwise intercoat adhesion will be impaired.

HEALTH & SAFETY INFORMATION

Please read and make sure you understand the relevant Material Safety Data Sheets.

All descriptions are based on the results of long term tests carried out in our laboratories and are believed to be true and accurate. No condition or warranty is given covering the results from the use of our products in any particular case, whether the purpose is disclosed or not, and we cannot accept liability if the desired results are not obtained.

Copyright © 2002 by Belzona International Limited. All rights reserved. Certain portions of this work copyright © 1980-2001 by Belzona International Limited. No part of this work covered by the copyrights hereon may be reproduced or used in any form or by any means - graphic, electronic or mechanical including photocopying, recording, taping or information storage and retrieval systems - without written permission of the publisher. Belzona® is a registered trademark

Belzona® 1141 - Instructions For Use - (Page 2)

Printed in England Publication No. 12-6-02

Belzona Polymerics Ltd.,
Claro Road,
Harrogate, HG1 4AY, England.
Tel: +44 (0) 1423 567641
Fax: +44 (0) 1423 505967
E-Mail: belzona@belzona.co.uk

Belzona Inc.,
2000 N.W. 88 Court,
Miami, Florida 33172, U.S.A.
Tel: +1 (305) 594 4994
Fax: +1 (305) 599 1140
E-Mail: belzona@belzona.com



BS EN ISO 9002 : 1994
Certificate No. Q09335



www.belzona.com