



BELZONA® 1391

INSTRUCTIONS FOR USE

1. TO ENSURE AN EFFECTIVE MOLECULAR WELD

- i) **METALLIC SURFACES - APPLY ONLY TO BLAST CLEANED SURFACES**
- a) Brush away loose contamination and degrease with a rag soaked in **Belzona® 9111** (Cleaner/Degreaser) or any other effective cleaner which does not leave a residue e.g. methyl ethyl ketone (MEK).
- b) Select an abrasive to give the necessary standard of cleanliness and a minimum depth of profile of 3 mils (75 microns).
Use only an angular abrasive.
- c) Blast clean the metal surface to achieve the following standard of cleanliness:
ISO 8501-1 Sa 2½ very thorough blast cleaning.
American Standard near white finish SSPC SP 10.
Swedish Standard Sa 2½ SIS 05 5900.
- d) After blasting, metal surfaces should be coated before any oxidation of the surface takes place.

SALT CONTAMINATED SURFACES

Metal surfaces that have been immersed for any periods in salt solutions e.g. sea water, should be blasted to the required standard, left 24 hours to allow any ingrained salts to sweat to the surface and then washed prior to a further brush blast to remove these. This process may need to be repeated to ensure complete removal of salts.

- ii) **SURFACES ALREADY REBUILT WITH BELZONA® 1311 (CERAMIC R-METAL).**
- a) If overcoating takes place within 2 hours, no further surface preparation is required.
- b) After this maximum overcoating time has elapsed roughen the **Belzona® 1311** preferably by brush blasting before applying **Belzona® 1391**.

2. COMBINING THE REACTIVE COMPONENTS

Transfer the entire contents of the Solidifier can into the Base module. Mix thoroughly together to achieve a uniform material free of any streakiness.

NOTES:

1. APPLICATION TEMPERATURE

Belzona® 1391 should NOT be applied at temperatures below 65°F (18°C).

2. WORKING LIFE

From the commencement of mixing, **Belzona® 1391** must be used within the times shown below.

Temperature	65°F (18°C)	75°F (24°C)	85°F (30°C)	105°F (40°C)
Use all material within	60 mins.	30 mins.	20 mins.	10 mins.

3. MIXING SMALL QUANTITIES

For mixing small quantities of **Belzona® 1391** use:
5 parts Base to 1 part Solidifier by volume
13 parts Base to 1 part Solidifier by weight.

4. VOLUME CAPACITY OF MIXED BELZONA® 1391

26.1 cu in (431 cm³) per kg.

3. APPLYING BELZONA® 1391

FOR BEST RESULTS

Do not apply when:

- i) The temperature is below 65°F (18°C) or the relative humidity is above 90%.
- ii) Rain, snow, fog or mist is present.
- iii) There is moisture on the metal surface or is likely to be deposited by subsequent condensation.
- iv) The working environment is likely to be contaminated by oil/grease from adjacent equipment or smoke from kerosene heaters or tobacco smoking.

(A) FOR SERVICE TEMPERATURES BELOW 212°F (100°C) BELZONA® 1391 IS APPLIED AS A SINGLE COAT SYSTEM AT 24-30 MILS.

Apply the **Belzona® 1391** directly on to the prepared surface with a stiff bristled brush or with the plastic applicator provided. To achieve the correct film thickness of 24-30 mils (600-750 microns), a practical coverage rate of 5.6 sq. ft (0.52 m²) per kg unit should be obtained.

TO ACHIEVE A UNIFORM COATING

- a) Apply the coating in one operation without interruption.
- b) In the area being treated by one unit of material, first "stripe coat" detail areas such as brackets, edges, corners and welds. Use a brush or applicator to initially wet out the substrate before building up to the full coating thickness over the complete area designated for that unit of material."
- c) Use a wet film thickness guage to regularly check that the correct film thickness is being achieved.
- d) Finish application with a brush to obtain uniform coverage.
- e) Ensure adequate lighting is available to prevent misses.

INSPECTION

- a) Immediately after application of each unit, visually inspect for pinholes and misses. Where detected these should be immediately brushed out.
- b) Once the application is complete and the coating has hardened, carry out a thorough visual inspection to confirm freedom from pinholes and misses, and to identify any possible mechanical damage.
- c) Where wet sponge testing is being used as an aid to confirm continuity of the coating, care should be taken to ensure that the surface is thoroughly wetted out by repeated passage of the sponge tester over the surface. The addition of a wetting agent such as detergent to the water used on the sponge will also assist. Under no circumstances should high voltage spark testing be used

**(B) FOR SERVICE TEMPERATURES
OF 212-265°F (100-130°C) BELZONA® 1391
IS APPLIED AT 32-40 MILS.**

Where application conditions permit, **Belzona® 1391** should be applied as a single coat as in (A) above, but at a thickness of 32-40 mils (800-1000 microns). To achieve the correct film thickness, a practical coverage rate of 4.2 sq. ft (0.39 sq. m) per kg unit should be obtained. Where it is not possible to achieve a uniform coating at this thickness, the material should be applied as a two coat system.

- a) Apply the first coat of **Belzona® 1391** as in (A) above and allow to harden for at least 16 hours.
- b) Brush away loose contamination and degrease with a rag soaked in **Belzona® 9111** (Cleaner/Degreaser) or any other effective cleaner which does not leave a residue e.g. methyl ethyl ketone (MEK).
- c) Carefully flash blast using a moderate blast pressure and fine grit to remove surface layer, but without significant loss of coating. A frosted appearance should be produced with a surface profile of 1 mil (25 microns) being ideal. Remove debris and degrease with **Belzona® 9111** or any other effective cleaner which does not leave a residue e.g. MEK.
- d) Apply a second coat of **Belzona® 1391** at a thickness of 12-15 mils (300-375 microns). To achieve the correct film thickness, a practical coverage rate of 11 ft² (1 m²) per kg unit should be obtained. **Belzona® 1391** is available in blue and gray, to facilitate application and to prevent misses. In service the colour of the applied product may change.

REPAIRS

Any misses, pinholes or mechanical damage found in the coating should be repaired by brush blasting or abrading the surface to produce a frosted appearance prior to application of further material as detailed above.

CLEANING

Mixing tools should be cleaned immediately after use with **Belzona® 9111** or any other effective solvent e.g. Methyl ethyl ketone (MEK). Brushes, injection guns, spray equipment and any other application tools should be cleaned using a suitable solvent such as **Belzona® 9121**, MEK, acetone or cellulose thinners.

4. COMPLETION OF THE MOLECULAR REACTION

Allow **Belzona® 1391** to solidify as below subjecting it to the conditions indicated.

Substrate temperature	Use involving no loading	Light loading	Cold water immersion	Hot water immersion*
65°F/18°C	5½ hours	9 hours	4 days	7 days
75°F/24°C	3½ hours	4½ hours	2½ days	4 days
85°F/30°C	2 hours	3 hours	2 days	3 days
105°F/40°C	1½ hours	2 hours	1½ days	2 days

NOTE:

Surface temperature should be above 18°C throughout the curing period.

* In certain instances it may be advantageous to post cure material prior to putting into service where chemical contact is involved. Refer to **Belzona® TKL** for specific recommendations.

5. FINAL SOLIDIFICATION OF BELZONA® 1391

When time is important and equipment usage is pressing, then by installing forced air heaters and taking steps to contain this heat around the equipment being reclaimed, final solidification time can be as little as 24 hours. Due allowance must be made for "warming up".

A final physical check can be made as precaution by taking a metal object and tapping the surface of the **Belzona® 1391**. Any partially solidified or soft spots will give a dull tone in relation to the metallic tone offered by solidified **Belzona® 1391**.

If there is any doubt regarding final solidification then **BE SAFE - MAKE MORE TIME.**

6. POST CURING TO OBTAIN OPTIMUM HEAT RESISTANCE

Although the heat resistance of **Belzona® 1391** cured at normal ambient temperatures is good, this can be improved dramatically by elevating the cure temperature.

This can be done prior to putting coated equipment into service by first allowing the coating to harden at ambient temperature for 24 hours prior to force curing at 212°F (100°C) for between 2 hours and 24 hours. This procedure should be adopted for any application when immediate exposure to a hot aggressive environment will occur.

Alternatively, the coating can be allowed to harden at ambient temperature for the time indicated in the "hot water immersion" column of the "Completion of the molecular reaction" table (see Section 4) and then put into service when any heat involved will advance the cure and enhance the heat resistance. This procedure is suitable for application where operating temperatures will be achieved gradually.

HEALTH & SAFETY INFORMATION

Please read and make sure you understand the relevant Material Safety Data Sheets.

All descriptions are based on the results of long term tests carried out in our laboratories and are believed to be true and accurate. No condition or warranty is given covering the results from the use of our products in any particular case, whether the purpose is disclosed or not, and we cannot accept liability if the desired results are not obtained.

Copyright © 2002 by Belzona International Limited. All rights reserved. Certain portions of this work copyright © 1980-2001 by Belzona International Limited. No part of this work covered by the copyrights hereon may be reproduced or used in any form or by any means - graphic, electronic or mechanical including photocopying, recording, taping or information storage and retrieval systems - without written permission of the publisher. Belzona® is a registered trademark

Belzona® 1391 - Instructions For Use - (Page 2)

Printed in England Publication No. 19-7-01

Belzona Polymerics Ltd.,
Claro Road,
Harrogate, HG1 4AY, England.
Tel: +44 (0) 1423 567641
Fax: +44 (0) 1423 505967
E-Mail: belzona@belzona.co.uk

Belzona Inc.,
2000 N.W. 88 Court,
Miami, Florida 33172, U.S.A.
Tel: +1 (305) 594 4994
Fax: +1 (305) 599 1140
E-Mail: belzona@belzona.com



BS EN ISO 9002 : 1994
Certificate No. Q09335



www.belzona.com