



# BELZONA® 2111 (D & A HI-BUILD ELASTOMER)

## INSTRUCTIONS FOR USE

### 1. TO ENSURE AN EFFECTIVE MOLECULAR WELD

#### a) SURFACE PREPARATION

##### (i) Metallic Surfaces

Remove all loose surface contamination and degrease with **Belzona® 9111** (Cleaner/Degreaser) or any other effective cleaner which does not leave a residue e.g. methyl ethyl ketone (MEK).

Grit blast to a minimum 3 mil (75 microns) profile. Where blasting is not practical, thorough mechanical grinding may be considered, except for applications involving tensile loads, such as expansion joints, and all applications involving immersion and/or fluid flow.

##### (ii) Flexible Surfaces (e.g. rubbers)

**NOTE:** **Belzona® 9111** can draw processing oils and waxes to the surface of some rubbers, particularly when new, which then impairs adhesion of **Belzona® 2111**. Test for this on a small area. If, on rubbing with a rag moistened with **Belzona® 9111**, a greasy film appears, the surface should not be degreased, but simply abraded.

Undercut fine edges with a sharp knife and scuff the surface with a rotary wire brush or suitable roughing tool.

- b) Brush away loose contamination and degrease again with **Belzona® 9111**.
- c) Immediately, apply a thin, even coat of **Belzona® 2911** or **Belzona® 2921** (Elastomer QD Conditioner) or (Elastomer GP Conditioner) onto the surface. A brush should be used as a stipple to ensure a practical coverage rate of 13 sq.ft (1.25 m<sup>2</sup>) per unit, on steel and most metallic substrates. On well roughened rubber substrates this could be reduced by as much as 50%

The **Belzona®** Conditioner must be touch dry before overcoating with **Belzona® 2111**. This will depend on the **Belzona®** Conditioner selected, prevailing temperature, relative humidity and substrate. At 68°F (20°C) and 50% relative humidity, the touch dry state will be achieved after the times given below when applied to a steel surface.

These times may be extended when applied to rubber substrates.

Conditioner	Touch Dry	Max. Overcoating
<b>Belzona® 2911</b>	20 min	4 hours
<b>Belzona® 2921</b>	2 hours	24 hours

Under no circumstances should application of **Belzona® 2111** take place after the maximum overcoating time.

When using **Belzona® 2111** to overcoat a surface which has been treated with a **Belzona® 1000** Series product (except **Belzona® 1221** (Super E-Metal), the **Belzona® 1000** Series product must first be allowed to fully cure, the surface prepared as outlined in section 1 (a) (i), and **Belzona® 2911** or **Belzona® 2921** applied as outlined in section 1 (c).

Application of **Belzona® 2111** over **Belzona® 1221** can be carried out up to 4 hours after the application of **Belzona® 1221** without the need of any surface treatment other than removal of contamination. When overcoating **Belzona® 1221** after this time, the surface should be abraded, followed by conditioning as in Section 1 (c).

#### WHERE BELZONA® 2111 SHOULD NOT ADHERE

Brush on a thin layer of **Belzona® 9411** (Release Agent) and allow to dry for 15 - 20 minutes before proceeding to step 2.

### 2. COMBINING THE REACTIVE COMPONENTS

**Both Base and Solidifier components must remain sealed until the application stage.**

- Empty the entire contents of the Base container into the mixing bowl provided.
- Shake the Solidifier container. Pour the contents over the Base in the mixing unit.
- Immediately mix together for at least 2 minutes and allow to stand until a gel forms (see table overleaf). Do not mix the material after this stage. Use all material within the times shown in the table overleaf

Temperature	41°F(5°C)	59°F(15°C)	77°F(25°C)	86°F(30°C)
Time to gel formation	10 min.	6 min.	3 min.	2 min.
Use all material within	25 min.	20 min.	12 min.	6 min.

N.B. These times are taken from the commencement of mixing.

#### NOTES:

- VOLUME CAPACITY OF MIXED BELZONA® 2111**  
28.5 cu.in. (468 cm<sup>3</sup>) per 500 g unit.
- COVERAGE RATE**  
1.95 sq.ft. (0.183 m<sup>2</sup>.) per unit at a thickness of 100 mil (2500 microns).

### 3. APPLYING THE BELZONA® 2111

#### FOR BEST RESULTS

##### Do not apply when:-

- The temperature is below 41°F(5°C) or the relative humidity is above 90%.
- Rain, snow, fog or mist is present.
- There is moisture on the surface or is likely to be deposited by subsequent condensation.
- The working environment is likely to be contaminated by oil/grease from adjacent equipment or smoke from kerosene heaters or tobacco smoking.

- Apply **Belzona® 2111** with the plastic spatula or applicator provided.
- Contour the **Belzona® 2111** to the correct profile with the plastic applicator provided.
- Smooth out contours to obtain the desired finish. For optimum results, apply the complete unit as quickly as possible. Once the material is spread as a thin film, the workable life is extended slightly to allow a more uniform finish to be obtained.

#### CLEANING

Mixing tools should be cleaned immediately after use with **Belzona® 9111** or any other effective solvent e.g. MEK. Application tools should be cleaned using a suitable solvent such as **Belzona® 9121**, MEK, acetone or cellulose thinners.

### 4. COMPLETION OF THE MOLECULAR REACTION

Allow **Belzona® 2111** to solidify as below before subjecting it to the conditions indicated:

	Movement or use involving no loading or immersion	Full mechanical or thermal loading	Immersion in chemicals
41°F/ 5°C	6 hours	3 days	5 days
50°F/10°C	4 hours	2 days	3½ days
59°F/15°C	3 hours	2 days	3 days
68°F/20°C	2 hours	1 day	2½ days
77°F/25°C	1½ hours	1 day	2 days
86°F/30°C	1 hour	1 day	1½ days

These times are for a thickness of approximately 0.10ins (2.5 mm); they will be reduced for thicker sections and extended for thinner sections.

### 5. STORAGE

Store in a dry environment at a temperature between 41°F (5°C) and 77°F (25°C).

Inadvertent storage of **Belzona® 2100** Base below 41°F (5°C) may result in partial solidification. If this occurs, the material can be restored to its normal form by resealing the container and warming to between 104°F (40°C) and 122°F (50°C) for three hours in a well ventilated, dry area.

**NOTE: Belzona® 2911** has an 18 month shelf life from date of manufacture when stored at 41 - 77°F (5 - 25°C) and must be used before the stated "use by" date.

### 6. OVERCOATING

Application of subsequent layers of **Belzona® 2111** can be carried out up to 3 days after the previous application without need of any surface treatment other than removal of contamination.

### HEALTH & SAFETY INFORMATION

Please read and make sure you understand the relevant Material Safety Data Sheets.

All descriptions are based on the results of long term tests carried out in our laboratories and are believed to be true and accurate. No condition or warranty is given covering the results from the use of our products in any particular case, whether the purpose is disclosed or not, and we cannot accept liability if the desired results are not obtained.

Copyright © 2002 by Belzona International Limited. All rights reserved. Certain portions of this work copyright © 1980-2001 by Belzona International Limited. No part of this work covered by the copyrights hereon may be reproduced or used in any form or by any means - graphic, electronic or mechanical including photocopying, recording, taping or information storage and retrieval systems - without written permission of the publisher. Belzona® is a registered trademark

### Belzona® 2111 - Instructions For Use - (Page 2)

Printed in England Publication No. 30-7-01

**Belzona Polymerics Ltd.**,  
Claro Road,  
Harrogate, HG1 4AY, England.  
Tel: +44 (0) 1423 567641  
Fax: +44 (0) 1423 505967  
E-Mail: belzona@belzona.co.uk

**Belzona Inc.**,  
2000 N.W. 88 Court,  
Miami, Florida 33172, U.S.A.  
Tel: +1 (305) 594 4994  
Fax: +1 (305) 599 1140  
E-Mail: belzona@belzona.com



BS EN ISO 9002 : 1994  
Certificate No. Q09335



[www.belzona.com](http://www.belzona.com)